



PURA NATURAL

Technical target values

Grammage (g/m²) ISO 536 (+ - 4%)	60	70	80	85	90
Brightness , index ISO 11475 CIE D65 (+ - 4)	93	93	93	93	93
Opacity, % ISO 2471 (+ - 2)	94	95	95,5	96	97
Bulk, cm³/g ISO 534	1,43	1,40	1,35	1,33	1,31
Smoothness	32	32	32	32	32
Moisture	6	6	6	6	6
Water Absorption	30	30	30	30	30

The values given are target values and variations occur