



PURA MATT

Target values subject to production variations. Updates will be done continuously.

Grammage g/m ² ISO 536 (+ - 4%)	90	100	115	130	150	170	200	250	300	350	400
Brightness, index ISO 11475 CIE D65 (+ - 4)	121,3	121,3	121,3	121,3	121,3	121,3	121,3	121,3	121,3	121,3	121,3
Opacity, % ISO 2471 (+ - 2)	92	93	95	96	97	97,5	-	-	-	-	-
Gloss, % ISO 8254-1 (+ - 5)	28	30	30	32	32	32	32	32	32	35	35
Bulk, cm ³ /g ISO 534	0,89	0,86	0,87	0,85	0,87	0,90	0,91	0,96	1,00	1,02	1,01
Humidity, % Tappi T502 (+ - 7)	50	50	50	50	50	50	50	50	50	50	50
Thickness, micron ISO 534 (+ - 5%)	80	86	100	111	131	153	181	239	299	358	405
Rugosity Parker, micron ISO 8791-4 (+ - 30%)	2,6	2,4	2,4	1,8	1,8	1,8	1,8	1,8	1,8	2,1	1,5

The values given are target values and variations occur

Produced by  LECTA



Il marchio della gestione
forestale responsabile
FSC® C107806



DBC PAPER SRL
offre prodotti certificati
PEFC

www.pefc.org