



## PURA GLOSS

Target values subject to production variations. Updates will be done continuously.

| Grammage g/m <sup>2</sup><br>ISO 536 (+ - 4%)     | 90   | 100  | 115  | 130  | 150  | 170  | 200  | 250  | 300  | 350  | 400  |
|---|------|------|------|------|------|------|------|------|------|------|------|
| Brightness, index<br>ISO 11475 CIE D65<br>(+ - 4) | 119  | 119  | 119  | 119  | 119  | 119  | 119  | 119  | 119  | 119  | 119  |
| Opacity, %<br>ISO 2471 (+ - 2)                    | 91   | 91,5 | 93   | 95,5 | 97   | -    | -    | -    | -    | -    | -    |
| Gloss, %<br>ISO 8254-1 (+ - 5)                    | 71   | 71   | 71   | 71   | 71   | 73   | 73   | 73   | 73   | 73   | 73   |
| Bulk, cm <sup>3</sup> /g<br>ISO 534               | 0,76 | 0,76 | 0,75 | 0,73 | 0,73 | 0,74 | 0,74 | 0,75 | 0,78 | 0,80 | 0,83 |
| Humidity, %<br>Tappi T502 (+ - 7)                 | 50   | 50   | 50   | 50   | 50   | 50   | 50   | 50   | 50   | 50   | 50   |
| Thickness, micron<br>ISO 534 (+ - 5%)             | 68   | 76   | 86   | 95   | 110  | 126  | 148  | 187  | 234  | 280  | 320  |

The values given are target values and variations occur